



# felters

ENGINEERING TEXTILES

SAE Grade No.	Lbs. per Sq. yd, 1"	Color	Wool Content	Tensile Strength	Shore A Hardness	Compression for 10% Deflection, psi	Vibration Absorption	Abrasion Resistance
F-1	16.0	White	95%	500	30-40	21	High	Excellent
F-2	16.0	Pink/Blk/Brown	90%	500	30-40	21	High	Excellent
F-3	16.0	Grey	85%	400	30-40	13	High	Excellent
F-5	12.24	White	95%	400	20-30	6	Medium	Good
F-7	12.24	Grey	80%	250	20-30	6	Medium	Good
F-10	8.48	White	95%	225	15-25	4	Low	Fair
F-11	8.48	Grey	87%	200	15-25	4	Low	Fair
F-13	8.48	Grey	75%	75	15-25	3	Low	Fair
F-15	8.48	Grey	55%	75	15-25	3	Low	Fair
F-26	7.20	Grey	45%	Not Rated	5-15	1	Very Low	Poor